

**Material inspection report (type 3.1. according to EN 10 204)**



Supplier: **Factory Address/Provozovna:**

Nanotex group s.r.o.  
Podkrusnohorska 271  
436 01 Litvinov  
Czech Republic

Customer:

Composition of the product:	PP spunbond/meltblown 37g/m <sup>2</sup>						
	Nanofibers layer of polymer PVDF						
	PP spunbond 20g/m2						
Product number: (customer reference nr.)	FMPV1900L	Production date:	n/a	Produced by:	J.Dvořák	original rolls width (mm):	N/A
Nanotex order:	n/a	Measurement date:	09.03.2020	Measured by:	P.Kozerich	original rolls lenght (mm):	N/A

Parameters	Nr.	average of 5th measurements	Standard	Measurement device	Measurement occurance	Roll number
Air Permeability at 200Pa	Guarantee	≥180 l/m2/s	EN ISO 9237	Textest 3300 FX	+/-3%	N/A
	Actual	185				
Filtration efficiency 0,3µm at 30l/min	Guarantee	≥ 80-92%	EN 1822	Palas MPF 2000	N/A	N/A
	Actual	85				

datum: 17.03.2020

approved by:

Petr Kozerich, Quality manager

